

# Supashield 25

## Description

Supashield 25 with a high CO<sub>2</sub> concentration displays excellent dip transfer performance on steel over 10mm in vertical and overhead positions.

It is the ideal choice for fast out-of-position welding of heavy sections and offers excellent root penetration and side fusion. Supashield 25 is particularly suited to the welding of heavy tubular sections.

Very heavy sections, deep penetration, low to medium spatter. The CO<sub>2</sub> content in these gases is ideal for welding galvanised metals.

## Applications

- MIG Welding of Mild and Carbon Manganese Steels
- Welding Thickness Range 6 - 50mm

## Hazard statement(s)

- Contains gas under pressure; may explode if heated.

## Prevention statement(s)

- None allocated.

## Response statement(s)

- None allocated.

## Storage statement(s)

- Protect from sunlight. Store in a well-ventilated place.

## Other hazards

- Asphyxiant. Effects are proportional to oxygen displacement.

Signal Word: Warning

UN No.: 1956

Hazard No.: 2TE

Chem Symbol: N/A

Classification: AS 4882-2003:  
SG-AC-23

Pictograms:



# Supashield 25

## General Specifications

Specifications	E Cyl.	G Cyl.	12 Pack
Cylinder/Pack (101.325kPa @15°C) - L	5.0	11.6	146.0
Water capacity per cylinder - L	23	50	600
Cylinder Colour	Peacock Blue/Green Grey Shoulder		
Outlet Connection	Type 10		
Package Dimensions (H x W x D) - mm	780 x 230	1,510 x 230	1,900 x 780 x 1,020

Cylinder dimensions are approximate – variations may occur due to manufacturing tolerances.  
 Height includes the valve. Container sizes may vary from state to state.

## Package Sizes Available



## Quality Assurance

Supagas Pty Ltd is committed to comply with the requirements of ISO 9001-2019 and to continually improve the effectiveness of our Quality Management System.

Everyone at Supagas understands we must provide a safe environment for both our employees and the wider community. We are therefore committed to implement and maintain a continual improvement approach throughout the organisation whilst also meeting all applicable statutory and regulatory requirements.

## For Further Information

On how we can help you with all your residential and industrial gas needs, view our website [supagas.com.au](http://supagas.com.au), call Customer Service on 13 78 72 or drop in to your local Supagas branch.

## Typical Analysis

Ar	CO <sub>2</sub>	O <sub>2</sub>	Tolerance on minor component mix.
Balance	25% +/- 2.5%	<20 ppm	+/- 10%